

IRON & STEEL SCRAP SPECIFICATIONS

Type of Scrap: **Borings**

ISRI Code: **223**
 ISRI name: **Iron borings**

Gerdau Code: **827**
 Gerdau name: **Borings**

Specifications

Clean cast iron or malleable iron borings and drillings, free of steel turnings, scale, lumps and organic liquids.

Expected Chemistry (%; max)

Copper	0.250
Chrome	0.150
Nickel	0.100
Tin	0.010
Phosphorous	0.050
Sulphur	0.110
Silicon	0.150
Molybdenum	0.050
Carbon	4.000

Dimension (inches; max)

Cambridge	N/A
Whitby	N/A
Manitoba	N/A
Perth Amboy	N/A
Sayreville	N/A
Knoxville	N/A
Jackson	N/A
Charlotte	N/A
Cartersville	N/A
Jacksonville	N/A
Wilton	N/A
St. Paul	N/A
Beaumont	N/A
Sand Springs	N/A

Pictures

